











## TECHNICAL CHARACTERISTICS EN

no. 703

Dry Pressed Ceramic tiles with low water absorption of Group BI<sub>a</sub>GL E ≤ 0,5%

Annex G, Universal tiles - GL

COLLECTION NAME	COLOUR	BODY	SURFACE
CALACATTA	GOLD, WHITE	NOT COLOUR BODY	POLISHED

PHYSICAL PROPERTIES		NORM	REQUIREMENTS	MEAN VALUE ACHIEVED	
	WATER ABSORPTION [%]	PN-EN ISO 10545-3	≤ 0,5	≤ 0,1	
	MODULUS OF RUPTURE [N/mm <sup>2</sup> ]	PN-EN ISO 10545-4	≥ 35	≥ 40	
	BREAKING STRENGTH [N]	PN-EN ISO 10545-4	> 1300	> 2100	
	FROST RESISTANCE	PN-EN ISO 10545-12	required	resistant	
	ABRASION RESISTANCE	PN-EN ISO 10545-7	required	GOLD	4/12000
				WHITE	4/12000
	RESISTANCE TO HOUSEHOLD CHEMICALS	PN-EN ISO 10545-13	min. B	Ammonium chloride solution	A
				Sodium hypochlorite solution	A
	RESISTANCE TO HIGH OR LOW CONCENTRATION OF ACIDS OR ALKALIS	PN-EN ISO 10545-13	declared	Hydrochloric acid solution, 3%	LA
				Citric acid solution 100g/l	LA
				Potassium hydroxide solution, 30g/l	LB
				Hydrochloric acid solution, 18%	HA
				Lactic acid solution, 5%	HA
Potassium hydroxide solution, 100g/l	HB				
	RESISTANCE TO STAINING	PN-EN ISO 10545-14	min. 3	4	
	CRAZING RESISTANCE	PN-EN ISO 10545-11	required	resistant	
<b>DCOF</b>	Dynamic Coefficient of Friction	ANSI A326.3	> 0,42	< 0,42	
	THERMAL SHOCK RESISTANCE	PN-EN ISO-10545-9	required	resistant	

REFERENCE DOCUMENT: DECLARATION OF PERFORMANCE NO. 7D/02 CPR

Signed for and on behalf of the manufacturer by:

TECHNOLOG

Piotr Szecha